



Spatially Targeted Activation of a SMP Based Reconfigurable Skin System

PI Dr. Gregory Reich
Co-PI Dr. James Joo
AFRL/RQ, WPAFB, OH, USA
Co-PI Dr. Richard Beblo
UDRI/AM, Dayton, OH, USA

Research Associates
Mr. Brian Smyers, AFRL/RQ, WPAFB, OH, USA
Mr. John Puttmann, UDRI/AM, Dayton, OH, USA

Case 88ABW-2012-4175 DISTRIBUTION A. Approved for public release; distribution is unlimited.

maintaining the data needed, and of including suggestions for reducing	ompleting and reviewing the collect this burden, to Washington Headqu uld be aware that notwithstanding ar	o average 1 hour per response, inclu- ion of information. Send comments arters Services, Directorate for Infor ny other provision of law, no person	regarding this burden estimate mation Operations and Reports	or any other aspect of the 1215 Jefferson Davis	is collection of information, Highway, Suite 1204, Arlington		
1. REPORT DATE AUG 2012		2. REPORT TYPE		3. DATES COVE 00-00-2012	red 2 to 00-00-2012		
4. TITLE AND SUBTITLE			5a. CONTRACT	NUMBER			
Spatially Targeted	ıble Skin	5b. GRANT NUMBER					
System			5c. PROGRAM ELEMENT NUMBER				
6. AUTHOR(S)			5d. PROJECT NUMBER				
		5e. TASK NUMBER					
			5f. WORK UNIT NUMBER				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Air Force Research Laboratory, AFRL/RQ, Wright Patterson AFB, OH, 45433					8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)					10. SPONSOR/MONITOR'S ACRONYM(S)		
			11. SPONSOR/MONITOR'S REPORT NUMBER(S)				
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited							
Grantees'/Contrac	nd Multifunctional M tors' Meeting for A	Materials for Defens FOSR Program on I 2012 in Arlington, V	Mechanics of Mu	ltifunctional	Materials &		
14. ABSTRACT							
15. SUBJECT TERMS							
16. SECURITY CLASSIFIC	17. LIMITATION OF	18. NUMBER	19a. NAME OF				
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified	Same as Report (SAR)	OF PAGES 17	RESPONSIBLE PERSON		

Report Documentation Page

Form Approved OMB No. 0704-0188




Overview





- Thermal
 - Thermal Modeling
 - Magnetic Modeling
 - Particle Alignment
- Mechanical
 - SMP Characterization
 - Constitutive Model
 - Geometry Optimization
- Future Work
- Summary





RQ Tech Division Consolidation




Adaptive Structures Team

Aerospace Vehicles







Power and Control














Rocket Propulsion





High Speed Systems









Turbine Engine








Project Overview



Adaptive Structures Tean





Heating Options




	Strain Capability	Corrosion Resistance	Conductivity	Manufacturability
NiChrome Mesh				
Permalloy80 Particle Chains				
Permalloy80 Random Particles				
NiChrome Wire Coils				
Stainless Steel Wool				
Constantine Wool				
Nickel Random Particles				
Nickel Particle Chains				





Thermal: Modeling












- Surface temp of chain limited to service temp of SMP
- Reduction in power required to prevent damage to SMP
- Builds on previous results of temperature varying thermal properties



Thermal: Magnetic Alignment of Particles





Magnetic Field Lines b/t Ni Particles


JS Leng, WM Huang, X Lan, YJ Liu, SY Du, Significantly reducing electrical resistivity by forming conductive Ni chains in a polyurethane shape memory polymer/carbon black composite, Applied Physics Letters, vol. 92, 2008




Thermal: Magnetic Alignment of Particles




Adaptive Structures Tean




End View of Permalloy80




Side View Permalloy80



End View of Nickel



Side View Nickel



End View of Particle Chains



Thermal: Current Results



Material	Diameter	Resistivity (Ω)	Comments
Permalloy80 Particles (random)	~37 μm		Oxidized
Permalloy80 Particles (aligned)	~37 µm		Oxidized
Ni-Cr Coil	0.3 mm	NA	Difficult to Manufacture
Nickel Particles (random)	3-7 μm	80	Viable Option
Stainless Steel Wool	0.08 mm	65	Viable Option
Nickel Particles (aligned)	3-7 μm	18	Viable Option
Constantine Wire Wool	0.02 mm	11.4	Viable Option
Ni-Cr Mesh	0.25 mm	0.4	Too Rigid



Mechanical: SMP Characterization



Adaptive Structures Team

Epoxy SMP Formulation

0.02 mol (7.28g) EPON 826 0.01 mol (2.3g) Jeffamine D230 100°C for 1.5hr, 130°C for 1hr


Experimental Results

T_g 65 °C E (ambient) 1400 MPa E (115 °C) 32 MPa

Values consistent over several batches, 0-8 week sample age



Epoxy SMP Characterization






Mechanical: System Mechanics Model



Filled Honeycomb Mechanics – In-plane Modulus



$$E_{cx} = B_1 E_h + B_2 E_i$$

$$E_{cy} = D_1 E_h + D_2 E_i$$

 B_1 , D_1 calculated using strain energy and deformation of honeycomb

B₂, D₂ calculated using strain energy from deformation of infill

Deformation of infill and honeycomb matched to give E_{cx} and E_{cy}

$$B_{1} = \frac{12I(a+x_{0})}{cly_{0}^{2}\left(y_{0} + \frac{12I\cos^{2}(\theta)}{y_{0}A} + \frac{6Ia}{y_{0}lA}\right)} \qquad B_{2} = \frac{(a+x_{0})K}{2y_{0}\beta^{2}(1-v_{i}^{2})}$$

$$D_{1} = \frac{12Iy_{0}}{c(a+x_{0})\left(lx_{0}^{2} + \frac{12Iy_{0}\sin(\theta)}{A}\right)} \qquad D_{2} = \frac{y_{0}K}{2(a+x_{0})(1-v_{i}^{2})}$$

$$\frac{12Iy_0}{c(a+x_0)\left(lx_0^2 + \frac{12Iy_0\sin(\theta)}{A}\right)}$$

$$B_2 = \frac{(a + x_0)K}{2y_0\beta^2(1 - v_i^2)}$$

$$D_2 = \frac{y_0 K}{2(a + x_0)(1 - v_i^2)}$$


$$K = \beta^3 - \gamma \beta^3 + \frac{\gamma^2 \beta^3}{2} \ln \left(1 + \frac{2}{\gamma} \right) + \frac{1}{\beta} + \frac{\gamma}{\beta} + 2\nu_i \beta \qquad \beta = \frac{y_0}{x_0} \qquad \gamma = \frac{a}{x_0}$$



Mechanical: System Mechanics Model




Adaptive Structures Tean




If
$$E_i = E_h$$

Then $E_{cx} = E_{cy} = E_h$



$$E_{cx} = B_1 E_h + (1 - B_1) E_i$$

$$E_{cy} = D_1 E_h + (1 - D_1) E_i$$







Mechanical: System Mechanics Model





Adaptive Structures Team

$$E_{cx} = B_1 E_h + (1 - B_1) E_i$$
 $E_{cy} = D_1 E_h + (1 - D_1) E_i$











System Effort: Geometry Optimization



Adaptive Structures Team

Geometry/Environment

Plate: 0.508 x 0.381 m

Load: 19 kN/m²

Matlab Optimtool Constraints

$$δ = 2.5 \text{ mm}$$
 $55^{\circ} ≤ θ ≤ 75^{\circ}$
 $d ≥ 0.2 \text{ mm}$
 $l,a ≤ 100 \text{ mm}$

Objective Function $Min(E_{cx} + E_{cy})$

<u>Design variables</u>


a, I, d, θ

$$\int_{l=1.619 \text{ mm}} \theta = 75^{\circ}$$

$$d = 0.201 \text{ mm}$$

$$a = 5.214 \text{ mm}$$

 $E_{cv} = E_{cx} = 1.55 \text{ GPa}$





Future Work



225.0 205.0

- 185.0

- 165.0

- 145.0 - 125.0 - 105.0 - 85.0

> 65.0 45.0

25.0

Adaptive Structures Tear

Thermal

Aligned Nickel Particle Electrical Resistance
Thermal Imaging (Speed and Uniformity of Heat)

Mechanical

Static Testing of Various Geometries of Honeycomb to Substantiate Models

Static Testing of Filled Honeycombs

Add Shear Modulus and Poisson's Ratio to Geometry Model

Continue Refinement of Optimization Model

FEA Analysis of Filled Honeycomb (Single Cell and Sheet w/ Heating Pattern)

System

Optimization of Multiple Reconfigurable Shapes

Fabrication of Entire System (Flexible Electrodes, Wiring, etc.)


Scaled Pressure Test of Optimized System

Major Milestones

- Characterization of custom SMP
- Thermal model suggests densely packed small wire-like heaters
- Magnetically aligned particle chain heaters promising
- Promising, more accurate composite mechanics model
- Optimization underway of unit cell

Major Challenges

- System integration/wiring/manufacturing
- Composite testing substantiating mechanics model
- Optimization of composite/cell heating pattern







Spatially Targeted Activation of a SMP Based Reconfigurable Skin System

Thank You

Gregory Reich James Joo Brian Smyers Richard Beblo John Puttmann

Case 88ABW-2012-4175 DISTRIBUTION A. Approved for public release; distribution is unlimited.